




NanOxiMet


Primary Particle Size Analysis (SEM)

Material	NM103
Date	2015/01/12
Particle Morphology	Spherical to elongated
Mean Diameter (nm)	34.0 nm \pm 8.2 nm
Mode Diameter (nm)	30.8 nm
Sigma (fit)	$\sigma = 1.27$
Comments	The observed particles and agglomerates /aggregates are well dispersed over the drying area on the substrate.
Short description	NM 103 consists of near-spherical to elongated particles with a mean diameter of approximately 34 nm. The particles tend to form relatively compact agglomerates or even aggregates.


Histogram



SEM Image (low magnification)



SEM Image (medium magnification)



SEM Image (high magnification)

